(19) World Intellectual Property Organization

International Bureau



(43) International Publication Date 15 January 2004 (15.01.2004)

PCT

(10) International Publication Number WO 2004/006016 A3

(51) International Patent Classification⁷: G03F 1/14, 1/08

(21) International Application Number:

PCT/IB2003/002939

13 June 2003 (13.06.2003) (22) International Filing Date:

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data: 0215243.7

2 July 2002 (02.07.2002)

(71) Applicant (for all designated States except US): KONIN-KLIJKE PHILIPS ELECTRONICS N.V. [NL/NL]; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).


(72) Inventors; and

(75) Inventors/Applicants (for US only): FRENCH, Ian, D. [GB/GB]; c/o Philips Intellectual Property & Standards, Cross Oak Lane, Redhill, Surrey RH1 5HA (GB). HEWETT, James [GB/GB]; c/o Philips Intellectual Property & Standards, Cross Oak Lane, Redhill, Surrey RH1 5HA (GB).

- (74) Agent: SHARROCK, Daniel, J.; Philips Intellectual Property & Standards, Cross Oak Lane, Redhill, Surrey RH1 5HA (GB).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: MASK AND MANUFACTURING METHOD USING MASK



(57) Abstract: A mask 12 includes half-tone layer 16 and light blocking layer 20. The half-tone layer 16 is of silicon rich silicon nitride SiN_x:H. x may be in the range 0 to 1, preferably 0.2 to 0.6, so that the optical band gap can be in the range 2.1eV to 2.5eV. It has been discovered that photoresist removal when the mask 12 is used is very dependent on the band gap, and not too dependent on the thickness, so good control of TFT manufacture can be obtained.